

Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) In-plane quasi-isotropic fiber reinforced resin composite material having a reduced or low coefficient of linear expansion that approaches substantially zero by combining sheets woven by one kind or more than one kind of reinforcing fibers, each coefficient of linear expansion of said sheets being controlled to be balanced by combining a matrix resin and two or more kinds of reinforcing fibers wherein said reinforcing fibers include at least one kind of reinforcing fibers having a negative coefficient of linear expansion or all of the reinforcing fibers have a negative coefficient of linear expansion, wherein said matrix resin is used to control the coefficient of linear expansion of the composite material such that said coefficient approaches substantially zero.

2. (Previously Presented) In-plane quasi-isotropic fiber reinforced resin composite material having a reduced or low coefficient of linear expansion that approaches substantially zero as claimed in claim 1, said material characterized in that monofilament, yarn doubling or blending

strand is used for said two or more kinds of reinforcing fibers.

3. (Previously Presented) In-plane quasi-isotropic fiber reinforced resin composite material having a reduced or low coefficient of linear expansion that approaches substantially zero as claimed in claim 1, wherein said coefficient of linear expansion is reduced by combining sheets woven by one or more kinds of reinforcing fibers of which a coefficient of linear expansion is controlled by a three dimensional structure of twisted yarn, biaxial textile or triaxial textile.

4. (Currently Amended) In-plane quasi-isotropic fiber reinforced resin composite material having a reduced or low coefficient of linear expansion that approaches substantially zero by combining sheets with different coefficients of linear expansion woven by one or more kinds of reinforcing fibers, wherein each coefficient of linear expansion of said reinforcing fibers is controlled to be balanced by combining a matrix resin and two or more kinds of reinforcing fibers wherein at least one kind of said reinforcing fibers has a negative coefficient of linear expansion or all of the reinforcing fibers have a negative coefficient of linear expansion, wherein said matrix resin is

used to control the coefficient of linear expansion of the composite material such that said coefficient approaches substantially zero.

5-6. (Cancelled)

7. (Currently Amended) In-plane quasi-isotropic fiber reinforced resin composite material having a reduced or low coefficient of linear expansion that approaches substantially zero as claimed in claim 2, wherein said coefficient of linear expansion is reduced by combining sheets woven by more than one kind of reinforcing fibers of which a coefficient of linear expansion is controlled by three dimensional structure of twisted yarn, biaxial textile or triaxial textile.

8-20. (Cancelled)

21. (Previously Presented) The fiber reinforced resin composite material of claim 1 wherein different sheets of reinforcing fibers have different coefficients of linear expansion.

22. (Previously Presented) The fiber reinforced resin composite material of claim 3 wherein different sheets of reinforcing fibers have different coefficients of linear expansion.

23. (Previously Presented) The fiber reinforced resin composite material of claim 4 wherein each of said two or more kinds of reinforcing fibers have different coefficients of linear expansion.

24-27. (Cancelled).

28. (Previously Presented) The fiber reinforced resin composite material of claim 1 wherein at least one of said sheets is at least partly woven of carbon fibers or polyparaphenylene benzo oxazale.

29. (Previously Presented) The fiber reinforced resin composite material of claim 3 wherein at least one of said sheets is at least partly woven of carbon fibers or polyparaphenylene benzo oxazale.

30. (Previously Presented) The fiber reinforced resin composite material of claim 4 wherein at least one of said sheets is at least partly woven of carbon fibers or polyparaphenylene benzo oxazale.

31-32. (Cancelled)